

TEST REPORT

No. : GZIN2007038435CM



Date : Aug 13, 2020 Page: 1 of 3

CUSTOMER NAME:	SAUDI SCAFFOLDING FACTORY	GZIN2007038
ADDRESS:	ABT BLDG., SALAHUDDIN AYYOUBI STREET AI-BUSTAN DIS	TRICT,
	OPP. AI NASEEM VILLAGE COMPOUND OFF KHOBAR-DAMM	AM
	EXPRESSWAY, KINGDOM OF SAUDI ARABIA	

Sample Name : SF BOARD RETAINING CLAMP 72001704

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

*	*	*	*	*	*	*	*	*	*	

Date of Receipt	:	Jul 27, 2020
Testing Start Date	:	Jul 27, 2020
Testing End Date	:	Aug 13, 2020
Test result(s)	:	For further details, please refer to the following page(s) (Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services Co., Ltd. GZ Branch Testing Center

Tobby Yang Authorized signatory



angzhou, China. 510663 t (86–20) 8215555 f (86–20) 82075080 www.sgsgroup.com.cn 邮编: 510663 t (86–20) 8215555 f (86–20) 82075080 e sgs.china@sgs.com 198 Kez omic & Technical Deve ad, Scientech Park, Ec nt District. G 中国・广州・经济技术开发区科学城科珠路198号

Member of the SGS Group (SGS SA)



TEST REPORT

No. : GZIN2007038435CM Date : Aug 13, 2020 Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Failure Force	With Reference to EN 74-1:2005	29.8kN	/

Note: Pass : Meet the requirements;

Fail : Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.agp.and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.agp.and, for electronic format document, advised that information contained hereon reflects the Company's indings at the time of its intervention only and within the limits of transaction from exercising all their rights and obligations under the transaction document. This document be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention is test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only. Attention: Check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-75) 8307 1443, or email: CN.Doccheck@sgs.com

1445, do Britan : Or Doctorio Langa good Control and Control (1997) (1



TEST REPORT

No. : GZIN2007038435CM Date : Aug 13, 2020 Page: 3 of 3

Test Item: Failure Force

Test Method: With Reference to EN 74-1:2005

Test Condition:

Specimen: Board retaining coupler, 5pcs

Test rate: 2mm/min


Test Result:

Test Item	Test Result						
restriction	1#	2#	3#	4#	5#	F _{p,5%} /γR2	
Failure Force(kN)	42.84	38.89	43.60	42.91	40.79	29.8	

Note:

- 1. $F_{p,5\%}$: the 5% quantile for the 75% level of confidence.
- 2. γ R2=1.25 according to EN 74-1.
- 3. Specification of steel bar for failure force: steel bar of Φ 48.3mm.

Test photo(s):



Appendix information: The above test was carried out by SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd.

******** End of report*******



Unless otherwise agreed in writing, this document is issued b overleaf, available on request or accessible at http://www.sgs.co subject to Terms and Conditions for Electronic Documents at f	m/en/Tern	ns-and-Conditions.aspx and, for ele	ctronic format documents,
Attention is drawn to the limitation of liability, indemnification a advised that information contained hereon reflects the Compan	and jurisdi	tion issues defined therein. Any h	older of this document is
Client's instructions, if any. The Company's sole responsibility transaction from exercising all their rights and obligations und except in full, without prior written approval of the Company. appearance of this document is unlawful and offenders may be p results shown in this testreport refer only to the sample(s) lested Attention:To check the authenticity of testing / inspection i 1443, or email: CN.Doccheck@sgs.com	y is to its ler the tra Any unaut prosecute and such	Client and this document does n nsaction documents. This docume horized alteration, forgery or fals d to the fullest extent of the law. Up sample(s) are retained for 30 days	ot exonerate parties to a int cannot be reproduced flication of the content or pless otherwise stated the only.
198 Kezhu Road, Scientech Park, Economic & Technical Development District, Guangzhou, China.	510663	t (86-20) 82155555 f (86-20) 820750	30 www.sgsgroup.com.cn
中国・广州・经济技术开发区科学城科珠路198号 邮编:	510663	t (86-20) 82155555 f (86-20) 820750	80 é sas.china@sas.com